

CARBON STEEL AND ALLOYED STEEL FOR STRUCTURAL USE

Type		International	Germany	France	Russia	Great Britain	USA	Japan
		ISO	DIN	BS	ГОСТ	DIN DIN/EN	AISI SAE	JIS
Carbon steel		C10	C10E - C10R	C10E - C10R	-	C10E - C10R	1010	S10C
		C15E4 - C15M2	C15E - C15R	C15E - C15R	-	C15E - C15R	1015	S15C
		-	C22 - C22E - C22R	C22 - C22E C22R	-	C22 - C22E C22R	1020	S20C
		C25 - C25E4 C25M2	C25 - C25E - C25R	C25 - C25E C25R	-	C25 - C25E C25R	1025	S25C
		C30 - C30E4 C30M2	C30 - C30E - C30R	C30 - C30E C30R	-	C30 - C30E C30R	1030	S30C
		C35 - C35E4 C35M2	35 - C35E - C35R	35 - C35E C35R	-	35 - C35E C35R	1035	S35C
		C40 - C40E4 C40M2	40 - C40E - C40R	40 - C40E C40R	-	40 - C40E C40R	1039 - 1040	S40C
		-	-	-	-	080A42	1042 - 1043	S43C
		C45 - C45E4 C45M2	45 - C45E - C45R	45 - C45E C45R	-	45 - C45E C45R	1045 - 1046	S45C
		-	-	-	-	-	-	S48C
		C50 - C50E4 C50M2	50 - C50E - C50R	50 - C50E C50R	-	50 - C50E C50R	1049	S50C
		-	-	-	-	-	1050 - 1053	S53C
		C55 - C55E4 C55M2	55 - C55E - C55R	55 - C55E C55R	-	55 - C55E C55R	1055	S55C
		C60 - C60E4 C60M2	60 - C60E - C60R	60 - C60E C60R	-	60 - C60E C60R	1059 - 1060	S58C
Alloy steel	Nickel chromium steel	-	-	-	40XH	-	-	SNC236
		-	-	-	-	-	-	SNC415(H)
		-	-	-	30XH3A	-	-	SNC631(H)
		15NiCr13	15NiCr13	15NiCr13	-	15NiCr13	-	SNC815(H)
		-	-	-	-	-	-	SNC836
	Nickel chromium	20NiCrMo2 20NiCrMoS2	20NiCrMo2-2 20NiCrMoS2-2	20NiCrMo2-2 20NiCrMoS2-2	-	20NiCrMo2-2 20NiCrMoS2-2	8615 8617(H) 8620(H) 8622(H)	SNCM220
		41CrNiMo2 41CrNiMoS2	-	-	-	-	8637 8640	SNCM240
		-	-	-	-	-	-	SNCM415
		-	-	-	20XH2M(20XHM)	-	4320(H)	SNCM420(H)
		-	-	-	-	-	-	SNCM431
		-	-	-	-	-	4340	SNCM439
		-	-	-	-	-	-	SNCM447
		-	-	-	-	-	-	SNCM616
		-	-	-	-	-	-	SNCM625
-	-	-	-	-	-	SNCM630		
-	-	-	-	-	-	SNCM815		

Note: The above chart is based on published data and not authorized by each manufacturer.



HARRY HERSBACH TOOLS BV
specialist in machining tools



ALLOYED STEEL

Type		International	Germany	France	Russia	Great Britain	USA	Japan	
		ISO	DIN	BS	ГОСТ	DIN DIN/EN	AISI SAE	JIS	
Carbon steel Alloy steel	Carbon steel	-	17Cr3 - 17CrS3	17Cr3 - 17CrS3	15X - 15XA	17Cr3 - 17CrS3	-	SCr415(H)	
		20Cr4(H) - 20Cr4	-	-	20X	-	5120(H)	SCr420(H)	
		34Cr4 - 34CrS4	34Cr4 - 34CrS4	34Cr4 - 34CrS4	30X	34Cr4 - 34CrS4	5130(H) - 5132(H)	SCr430(H)	
		34Cr4 - 34CrS4 37Cr4 - 37CrS4	37Cr4 37CrS4	37Cr4 37CrS4	35X	37Cr4 37CrS4	5132	SCr435(H)	
		37Cr4 - 37CrS4 41Cr4 - 41CrS4	41Cr4 41CrS4	41Cr4 41CrS4	40X	530M40 - 41Cr4 41CrS4	5140(H)	SCr440(H)	
		-	-	-	45X	-	-	SCr445(H)	
	Chromium molybdenum steel	-	-	-	-	-	-	-	SCM415(H)
		18CrMo4 18CrMoS4	18CrMo4 18CrMoS4	18CrMo4 18CrMoS4	20XM	18CrMo4 18CrMoS4	-	SCM418(H)	
		-	-	-	20XM	708M20 (708H20)	-	SCM420(H)	
		-	-	-	30XM - 30XMA	-	4130	SCM430	
		-	-	-	-	-	-	SCM432	
		34CrMo4 34CrMoS4	34CrMo4 34CrMoS4	34CrMo4 34CrMoS4	35XM	34CrMo4 34CrMoS4	4137(H)	SCM435(H)	
		42CrMo4 42CrMoS4	42CrMo4 42CrMoS4	42CrMo4 42CrMoS4	-	42CrMo4 42CrMoS4	4140(H) 4142(H)	SCM440(H)	
		-	-	-	-	-	4145(H) - 4147(H)	SCM445(H)	
	Manganese steel and manganese chromium steel	22Mn6(H)	-	-	-	-	1522(H)	SMn420(H)	
		-	-	-	30Г2 - 35Г2	-	1534	SMn433(H)	
		36Mn6(H)	-	-	35Г2 - 40Г2	-	1541(H)	SMn438(H)	
		42Mn6(H)	-	-	40Г2 - 45Г2	-	1541(H)	SMn443(H)	
		-	-	-	-	-	-	SMnC420(H)	
		-	-	-	-	-	-	SMnC443(H)	
	Aluminium chromium molybdenum steel	41CrAlMo74	-	-	-	-	-	SACM645	

Note: The above chart is based on published data and not authorized by each manufacturer.



CHROMIUM MOLYBDENUM STEEL

Type		International	Germany	France	Russia	Great Britain	USA		Japan
		ISO	DIN DIN/EN	BS BS/EN	ГОСТ	DIN DIN/EN	UNS	AISI SAE	JIS
Stainless steel	Austenitic	X12CrMn-NiN17-7-5	-	Z12CMN17-07Az	-	-	S20100	201	SUS201
		X12CrMn-NiN18-9-5	-	-	12X17Г9AH4	284S16	S20200	202	SUS202
		X10CrNi18-8	X12CrNi17-7	Z11CN17-08	07X16H6	301S21	S30100	301	SUS301
		X2CrNiN18-7	X2CrNiN18-7	-	-	-	-	-	SUS301L
		-	X12CrNi17-7	-	-	-	-	-	SUS301J1
		-	-	Z12CN18-09	12X18H9	12X18H9	S30200	302	SUS302
		X12CrNi-Si18-9-3	-	-	-	-	S30215	302B	SUS302B
		X10CrNiS18-9	X10Cr-NiS18-9	Z8CNF18-09	-	303S25	S30300	303	SUS303
		-	-	-	12X12H10E	303S41	S30323	S30323	SUS303Se
		-	-	-	-	-	-	-	SUS303Cu
		X5CrNi18-9	X5CrNi18-10	X5CrNi18-10	08X18H10	304S31	S30400	304	SUS304
		X2CrNi18-9	X2CrNi19-11	Z3CN19-11	03X18H11	304S11	S30403	304L	SUS304L
		X5CrNiN18-8	-	X5CrNiN18-8	-	-	S30451	304N	SUS304N1
		-	-	-	-	-	S30452	-	S30452
		X2CrNiN18-9	X2CrNiN18-9	Z3CN18-10Az	-	-	S30453	S30453	SUS304LN
		-	-	-	-	-	-	-	SUS304J1
		-	-	-	-	-	-	-	SUS304J2
		-	-	-	-	-	S30431	S30431	SUS304J2
		X6CrNi18-2	X5CrNi18-12	Z8CN18-12	Z8CN18-12	305S19	S30500	305	SUS305
		-	-	-	-	-	-	-	SUS305J1
		-	-	Z10CN24-13	-	-	S30908	309S	SUS309S
		X6CrNi25-21	-	Z8CN25-20	10X23H18	310S31	S31008	310S	SUS310S
		-	-	-	-	-	-	-	SUS315J1
		-	-	-	-	-	-	-	SUS315J2
		X5CrNi-Mo17-12-2	X5CrNi-Mo17-12-2	Z7C-ND17-12-02	-	316S31	S31600	316	SUS316
		X3CrNi-Mo17-12-3	X5CrNi-Mo17-13-3	Z6C-ND18-12-03	-	-	-	-	SUS316F
		-	-	-	-	-	-	-	SUS316F

Vervolg tabel op volgende pagina
Continued table on next page



HARRY HERSBACH TOOLS BV
specialist in machining tools



CHROMIUM MOLYBDENUM STEEL

Type		International	Germany	France	Russia	Great Britain	USA		Japan	
		ISO	DIN DIN/EN	BS BS/EN	ГОСТ	DIN DIN/EN	UNS	AISI SAE	JIS	
Stainless steel	Austenitic	X2CrNi-Mo17-12-2	X2CrNi-Mo17-13-2 X2CrNi-Mo17-14-3	Z3CND17-12-02	03X17H14M3	316S11	S31603	316L	SUS316L	
		X2CrNi-Mo17-12-3		Z3CND17-12-03						
		X2CrNi-Mo18-14-3								
		-	-	-	-	-	S31651	316N	SUS316N	
		X2CrNi-MoN17-11-2	X2CrNi-MoN17-12-2 X2CrNi-MoN17-13-3	Z3CND17-11Az	-	-	S31653	316LN	SUS316LN	
		X2CrNi-MoN17-12-3		Z3CND17-12Az						
		X6CrNiMo-Ti17-12-2	X6CrNiMo-Ti17-12-2	Z6CNDT17-12	08X17H13M2T	-	S31635	-	SUS316Ti	
		-	-	-	-	-	-	-	SUS316J1	
		-	-	-	-	-	-	-	SUS316J1L	
		-	-	-	-	-	317S16	S31700	317	SUS317
		X2CrNi-Mo19-14-4	X2CrNi-Mo18-16-4	Z3CND19-15-04	-	317S12	S31703	317L	SUS317L	
		X2CrNi-MoN18-12-4	-	Z3CND19-14Az	-	-	S31753	-	SUS317LN	
		-	-	-	-	-	-	-	SUS317J1	
		-	-	-	-	-	-	-	SUS317J2	
		-	-	-	-	-	-	-	SUS317J3L	
		-	-	-	-	-	N08367	-	SUS836L	
		X1CrNiMo-Cu25-20-5	-	Z2NCUDU25-20	-	904S14	N08904	N08904	SUS890L	
		X6CrNiTi18-10	X6CrNi-Ti18-10	Z6CNT18-10	08X18H10T	321S31	S32100	321	SUS321	
		X6CrNiNb18-10	X6CrNiNb18-10	Z6CNNb18-10	08X18H125	347S31	S34700	347	SUS347	
		X3NiCr18-16	-	Z6CN18-16	-	-	S38400	384	SUS384	
X3CrNi-Cu18-9-4	-	Z2CNU18-10	-	394S17	S30430	304Cu	SUSXM7			
-	-	Z15CNS20-12	-	-	S38100	-	SUSXM15J1			

Vervolg tabel op volgende pagina
Continued table on next page



HARRY HERSBACH TOOLS BV
specialist in machining tools



CHROMIUM MOLYBDENUM STEEL

Type	International	Germany	France	Russia	Great Britain	USA		Japan		
	ISO	DIN DIN/EN	BS BS/EN	ГОСТ	DIN DIN/EN	UNS	AISI SAE	JIS		
Stainless steel	Austenitic ferritic	-	-	-	-	-	S32900	329	SUS329J1	
		X2CrNi-MoN22-5-3	-	Z3CN-DU22-05Az	-	08X21H6M2T	S31803	31803	SUS329J3L	
		X2CrNiMo-CuN25-6-3	-	Z3CN-DU25-07Az	-	-	S32250	32250	SUS329J4L	
	Ferritic	X6CrAl13	X6CrAl13	Z8CA12	-	405S17	S40500	405	SUS405	
		-	-	Z3C14	-	-	-	-	SUS410L	
		-	-	-	-	-	S42900	429	SUS429	
		X6Cr17	X6Cr17	Z8C17	12X17	430S17	S43000	430	SUS430	
		X7CrS17	X7CrS18	Z8CF17	-	-	S43020	430F	SUS430F	
		X3CrTi17 X3CrNb17	X6CrTi17	Z4CT17	-	-	S43035	-	SUS430LX	
		X2CrTi17	X6CrNb17	Z4CNb17	-	-	-	-	SUS430J1L	
		X6CrMo17-1	X6CrMo17-1	Z8CD17-01	-	434S17	S43400	434	SUS434	
		X1CrMoTi16-1	-	-	-	-	S43600	436	SUS436L	
		-	-	-	-	-	-	-	SUS436J1L	
		X2CrMoTi18-2	-	Z3CDT18-02	-	-	S44400	444	SUS444	
		-	-	-	-	-	-	-	SUS445J1	
		-	-	-	-	-	-	-	SUS445J2	
		-	-	-	-	-	S44700	-	SUS447J1	
		-	-	Z1CD26-01	-	-	S44627	-	SUSXM27	
		Martensitic	-	-	-	-	-	S40300	403	SUS403
			X12Cr13	X10Cr13	Z13C13	-	410S21	S41000	410	SUS410
	X6Cr13		X6Cr13	Z8C12	08X13	403S17	S41008	410S	SUS410S	
	-		-	-	-	-	-	-	SUS410F2	
	-		-	-	-	-	S41025	-	SUS410J1	
	X12CrS13		-	Z11CF13	-	416S21	S41600	416	SUS416	
	X20Cr13		X20Cr13	Z20C13	20X13	420S29	S42000	420	SUS420J1	
	X30Cr13		X30Cr13	Z33C13	30X13	420S37	S42000	420	SUS420J2	
	X29CrS13		-	Z30CF13	-	-	S42020	420F	SUS420F	
	-		-	-	-	-	-	-	SUS420F2	
	-		-	-	-	-	-	-	SUS429J1	

Vervolg tabel op volgende pagina
Continued table on next page



HARRY HERSBACH TOOLS BV
specialist in machining tools



CHROMIUM MOLYBDENUM STEEL

Type		International	Germany	France	Russia	Great Britain	USA		Japan
		ISO	DIN DIN/EN	BS BS/EN	ГОСТ	DIN DIN/EN	UNS	AISI SAE	JIS
Stainless steel	Martensitic	X19CrNi16-2	X20CrNi17-2	Z15CN16-02	20X17H2	431S29	S43100	431	SUS431
		X70CrMo15	-	Z70C15	-	-	S44002	440A	SUS440A
		X105CrMo17	-	-	-	-	S44003	440B	SUS440B
			-	Z100CD17	95X18	-	S44004	440C	SUS440C
	Precipitation hardening type	-	-	-	-	-	S44020	S44020	SUS440F
		X5CrNi-CuNb16-4	X7CrNiAl17-7	Z6CNU17-04	-	-	S17400	S17400	SUS630
		X7CrNiAl17-7	-	Z9CNA17-07	09X17H7Ю	-	S17700	S17700	SUS631
		-	-	-	-	-	-	-	SUS631J1
		-	-	-	-	-	-	-	-

Note: The above chart is based on published data and not authorized by each manufacturer.



HEAT RESISTANT STEEL

Type	International	USA	Japan
	ISO	AISI ATM	JIS
Alloy tool steel	-	-	SK140
	C120U	W1-11 1/2	SK120
	C105U	W1-10	SK105
	-	W1-9	SK95
	C90U	-	SK90
	-	W1-8	SK85
	C80U	-	SK80
	-	-	SK75
	C70U	-	SK70
	-	-	SK65
	-	-	SK60
	HS18-0-1	T1	SKH2
	-	T4	SKH3
	-	T5	SKH4
	-	T15	SKH10
	HS6-5-3-8	-	SKH40
	HS1-8-1	-	SKH50
	HS6-5-2	M2	SKH51
	HS6-6-2	M3-1	SKH52
	HS6-5-3	M3-2	SKH53
	HS6-5-4	M4	SKH54
	HS6-5-2-5	-	SKH55
	-	M36	SKH56
	HS10-4-3-10	-	SKH57
	HS2-9-2	M7	SKH58
	HS2-9-1-8	M42	SKH59
	-	F2	SKS11
	-	-	SKS2
	-	-	SKS21
	-	-	SK5
	-	L6	SKS51
	-	-	SKS7
	-	-	SKS81
-	-	SKS8	
-	-	SKS4	

Vervolg tabel op volgende pagina Continued table on next page



HEAT RESISTANT STEEL

Type	International	USA	Japan
	ISO	AISI ATM	JIS
Alloy tool steel	-	-	SKS41
	105V	W2-9 1/2	SKS43
	-	W2-8 1/2	SKS44
	-	-	SKS3
	-	-	SKS31
	-	-	SKS93
	-	-	SKS94
	-	-	SKS95
	X210Cr12	D3	SKD1
	X210CrW12	-	SKD2
	X153CrMoV12	-	SKD10
	-	D2	SKD11
	X100CrMoV5	A2	SKD12
	-	-	SKD4
	X30WCrV9-3	H21	SKD5
	-	H11	SKD6
	X40CrMoV5-1	H13	SKD61
	X35CrWMoV5	H12	SKD62
	32CrMoV12-28	H10	SKD7
	38CrCoWV18-17-17	H19	SKD8
	-	-	SKT3
55NiCrMoV7	-	SKT4	
45NiCrMo16	-	SKT6	

Note: The above chart is based on published data and not authorized by each manufacturer.



SPECIAL USE STEEL

Type	International	USA	Japan
	ISO	AISI ATM	JIS
Free cutting carbon steels	-	1110	SUM11
	-	1109	SUM12
	9S20	1212	SUM21
	11SMn28	1213	SUM22
	11SMnPb28	-	SUM22L
	-	1215	SUM23
	-	-	SUM23L
	11SMnPb28	12L14	SUM24L
	12SMn35	-	SUM25
	-	1117	SUM31
	-	-	SUM31L
	-	-	SUM32
	-	1137	SUM41
	-	1141	SUM42
	44SMn28	1144	SUM43
High carbon chromium steel	-	-	SUJ1
	B1	52100	SUJ2
	B2	ASTM A	SUJ3
	-	485	-
	-	Grade 1	-
	-	-	SUJ4
	-	-	SUJ5

Note: The above chart is based on published data and not authorized by each manufacturer.



CASTING AND FORGING STEEL

Type	International	Germany	France	Russia	Great Britain	USA	Japan
	ISO	DIN DIN/EN	BS BS/EN	ГОСТ	DIN DIN/EN	AISI ASTM	JIS
Carbon steel casting	200-400, 230-450, 270-480	GS-	GE230, GE280, GE320	-	A1, A2	U-	SC
Steel casting for welded structures	200-400W, 230-450W, 270-480W, 340-550W	-	GE230, GE280	-	A4	WCA, WCB, WCC	SCW
Heat resistant steel casting	GX40CrSi24, GX40CrNiSi22-10, GX40NiCr-Si38-19	-	GX40Ni-CrNb45-35, GX50NiCr-CoW35-25-15-5	-	309C30, 310C45, 330C12	Grade HC, HD, HF	SCH
Steel casting for high temperature and high pressure service	-	G20Mo5, G17CrMo5-5, G17CrMo5-10	G17CrMo9-10, GX15CrMo5, GP240GH, GP-280GH	-	A1, A2, B1, B2, B3, B4, B5, B7	Grade WC1, WC6, WC9	SCPH
Steel casting for low temperature and high pressure service	-	-	FB-M, FC1-M, FC2-M, FC3-M	-	AL1, BL2	Grade LCB, LC1, LC2, LC3	SCPL
Grey iron casting	100, 150, 200, 250, 300, 350	EN-GJL-	EN-GJL-	-	EN-GJL-	No. 20, 25, 30, 35, 40, 45, 50	FC
Spheroidal graphite iron casting	700-2, 600-3, 500-7, 450-10, 400-15, 400-18, 350-22	EN-GJS-	EN-GJS-	B4	EN-GJS-	60-40-18, 65-45-12, 8-55-06, 100-70-03, 120-90-02	FCD
Austempered spheroidal graphite iron casting	-	EN-GJS-	EN-GJS-	-	EN-GJS-	-	FCAD
Austenitic iron casting	L, S-	F1, F2, S2W, S5S	L, S-	-	F1, F2, S2W, S5S	Type 1, 2 Type D-2, D-3A Class 1, 2	FCA-FCDA-
Carbon steel forging for general use	-	C22, C25, C30, C35, C40, C45, C50, C55, C60	P245, P280, P305	-	C22, C25, C30, C35, C40, C45, C50, C55, C60	Class A, B, C, D, E, F	SF
Chromium molybdenum steel forgings for general use	-	-	-	-	-	Class E, F, G, I Grade 3A, 4 Class G, J, K, L, M	SFCM
Nickel chromium molybdenum steel forgings for general use	-	-	-	-	-	Class G, H, I, J Class 3A, 4, 5, 6 Class K, L, M	SFNCM

Note: The above chart is based on published data and not authorized by each manufacturer.



NON-FERROUS ALLOY

Type	International	Germany	Great Britain	USA	Japan
	ISO	DIN DIN/EN	DIN DIN/EN	AISI ASTM	JIS
Copper alloy, Nickel alloy	Copper alloy casting	-	-	-	CAC101
		-	Cu-C(CCO40AgradeC)	-	CAC102
		-	Cu-C(CCO40AgradeA,B)	-	CAC103
	Brass casting	-	CuZn15As-C(CC760S)	-	CAC201
		-	CuZn33Pb2-C(CC750S)	C85400	CAC202
		-	CuZn39Pb1-C(CC754S)	C85700	CAC203
	High strength brass casting	-	CuZn35Mn2Al1Fe-C(CC765S)	C86500	CAC301
		-	CuZn34Mn3Al2Fe1-C(CC764S)	C86400	CAC302
		-	CuZn25Al5Mn4Fe3-C(CC762S)	C86200	CAC303
		-	CuZn25Al5Mn4Fe3-C(CC762S)	C86300	CAC304
	Bronze casting	-	CuSn3Zn8Pb5-C(CC490K)	C84400	CAC401
		-	-	C90300	CAC402
		-	-	C90500	CAC403
		-	CuSn5Zn5Pb5-C(CC490K)	C83600	CAC406
		-	-	C92200	CAC407
	Phosphor bronze casting	-	CuSn10-C(CC480K) CuSn12-C(CC483K)	C90700 C90800	CAC502A
		-			CAC502B
		-			CAC503A
		-			CAC503B
	Aluminium bronze casting	-	CuAl10Fe2-C(CC331G)	C95200	CAC701
		-	CuAl10Ni3Fe2-C(CC332G)	C95400	CAC702
		-		C95410	
		-	CuAl10Fe5Ni5-C(CC333G)	C95800	CAC703
		-	-	C95700	CAC704
	Silicon bronze castings	-	-	-	CAC801
		-	-	C87500	CAC802
		-	CuZn16Si4-C(CC761S)	C87400	CAC803

Note: The above chart is based on published data and not authorized by each manufacturer.



NON-FERROUS ALLOY

Type	International	Germany	France	Great Britain	USA	Japan		
	ISO	DIN	BS	DIN	AISI	JIS		
Aluminium alloy	Aluminium alloy ingots for casting	Al-Cu4MgTi		EN AC-2100		204.0	AC1B	
		-		-		-	AC2A	
		-		-		319.0	AC2B	
		-		EN AC-44100		-	AC3A	
		-		-		-	AC4A	
		Al-Si8Cu3		EN AC-46200		333.0	AC4B	
		Al-Si7Mg(Fe)		EN AC-42000		356.0	AC4C	
		Al-Si7Mg0.3		EN AC-42100		A356.0	AC4CH	
		-		EN AC-45300		355.0	AC4D	
		Al-Cu4Ni2Mg2		-		242.0	AC5A	
		-		-		514.0	AC7A	
		Al-Si12CuNiMg		EN AC-48000		-	AC8A	
		-		-		-	AC8B	
		-		-		332.0	AC8C	
		-		-		-	AC9A	
	-		-		-	AC9B		
	Aluminium die casting	-		-		A413.0	ADC1	
		-		-		A360.0	ADC3	
		-		-		518.0	ADC5	
		-		-		-	ADC6	
		-		-		-	ADC10	
		-		-		A380.0	ADC10Z	
		-		-		-	ADC12	
		-		-		383.0	ADC12Z	
	Magnesium alloy	Magnesium alloy casting	-		-		AM100A	MC5
			-		-		ZK51A	MC6
-				-		ZK61A	MC7	
MgRE3Zn2Zr				EN MC65120		EZ33A	MC8	
MgAg3RE2Zr				EN MC65210		QE22A	MC9	
MgZn4RE1Zr				EN MC35110		ZE41A	MC10	
Magnesium alloy die casting		-		G-A9Z1Y4		AZ91A	MD1A	
		-		-		AZ91B	MDC1B	
		MgAl9Zn1{A}		EN MC21120		AZ91D	MDC1D	
		MgAl6Mn		EN MC21320		AM60B	MDC2B	

Vervolg tabel op volgende pagina
Continued table on next page



HARRY HERSBACH TOOLS BV
specialist in machining tools



NON-FERROUS ALLOY

Type		International	Germany	France	Great Britain	USA	Japan
		ISO	DIN	BS	DIN	AISI	JIS
Aluminium alloy	Aluminium alloy extruded shapes	-		EN AW-5052		5052	A5052S
		-		EN AW-5454		5454	A5454S
		AlMg4.5Mn0.7		EN AW-5083		5083	A5083S
		-		EN AW-5086		5086	A5086S
		AlMg1SiCu		EN AW-6061		6061	A6061S
		AlMg0.7Si		EN AW-6063		6063	A6063S
		-		EN AW-7003		-	A7003S
		-		-		-	A7N01S
		AlZn5.5MgCu		EN AW-7075		7075	A7075S

Note: The above chart is based on published data and not authorized by each manufacturer.

